

Australian Standard™

**Guidance on the measurement of
wettability of insulator surfaces**

This Australian Standard was prepared by Committee EL-010, Overhead Lines. It was approved on behalf of the Council of Standards Australia on 21 April 2005. This Standard was published on 24 May 2005.

The following are represented on Committee EL-010:

Australasian Railway Association
Australian Chamber of Commerce and Industry
Australian Electrical and Electronic Manufacturers Association
Australian Porcelain Insulators Association
Electricity Engineers Association (New Zealand)
Energy Networks Association

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Web Shop at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Global Standard*, has a full listing of revisions and amendments published each month.

Australian Standards™ and other products and services developed by Standards Australia are published and distributed under contract by SAI Global, which operates the Standards Web Shop.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.org.au, or write to the Chief Executive, Standards Australia, GPO Box 5420, Sydney, NSW 2001.

This Standard was issued in draft form for comment as DR 05022.

Australian Standard™

**Guidance on the measurement of
wettability of insulator surfaces**

First published as AS IEC 62073—2005.

COPYRIGHT

© Standards Australia

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia, GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 6706 0

PREFACE

This Standard was prepared by the Australian members of the Joint Standards Australia/Standards New Zealand Committee EL-010, Overhead Lines. After consultation with stakeholders in both countries, Standards Australia and Standards New Zealand decided to develop this Standard as an Australian, rather than an Australian/New Zealand Standard.

The objective of this Standard is to provide users and manufacturers of insulators with guidance on the measuring of wettability of insulator surfaces.

This Standard is identical with, and has been reproduced from IEC/TS 62073, Ed. 1.0 (2003), *Guidance on the measurement of wettability of insulator surfaces*.

As this Standard is reproduced from an International Standard, the following applies:

- (a) Its number does not appear on each page of text and its identity is shown only on the cover and title page.
- (b) In the source text 'this international standard' should read 'this Australian Standard'.
- (c) A full point should be substituted for a comma when referring to a decimal marker.
- (d) Any French text on figures should be ignored.

The terms 'normative' and 'informative' are used to define the application of the annex to which they apply. A normative annex is an integral part of a standard, whereas an informative annex is only for information and guidance.

CONTENTS

	<i>Page</i>
INTRODUCTION	v
1 Scope and object	1
2 Terms and definitions	1
3 Methods for measurement of wetting properties	3
4 Method A – Contact angle method	3
4.1 General	3
4.2 Equipment	4
4.3 Measurement procedure	4
4.3.1 General recommendations	4
4.3.2 Static contact angle measurements	4
4.3.3 Dynamic contact angle measurements	4
4.4 Evaluation	5
5 Method B – Surface tension method	5
5.1 General	5
5.2 Safety precautions	6
5.3 Equipment and reagents	6
5.3.1 Preparation of reagents	6
5.3.2 Equipment	6
5.4 Measurement procedure	6
5.5 Evaluation	7
6 Method C – The spray method	7
6.1 General	7
6.2 Equipment	7
6.3 Measurement procedure	7
6.4 Evaluation	8
7 Documentation	8
Annex A (normative) Guidelines regarding the applicability and comments on the limitations of the different methods described in this technical specification	10
Annex B (normative) Method A – Contact angle method	12
Annex C (normative) Method B – Surface tension method	13
Annex D (normative) Method C – Spray method	15
Figure 1 – Definition of the static contact angle	2
Figure 2 – Definition of the advancing angle (θ_a) and the receding angle (θ_r) inside a liquid drop resting on an inclined solid surface	3
Figure 3 – Measurements of the advancing angle (θ_a) and the receding angle (θ_r) by adding or withdrawing water from a droplet	5
Figure B.1 – Measurement of the advancing angle (θ_a) and the receding angle (θ_r) by using the captive bubble technique	12
Table 1 – Criteria for the determination of wettability class (WC)	8
Table C.1 – Concentrations of ethylene-glycol-monoethyl-ether (cellosolve), formamide mixtures used in measuring surface tension of insulator surfaces in the range 30 mN/m to 56 mN/m ($T = 20^\circ\text{C}$)	13

Table C.2 – Concentrations of distilled water and formamide mixture used in measuring surface tension of insulator surfaces in the range 58 mN/m to 73 mN/m ($T = 20^{\circ}\text{C}$) 14

Table C.3 – Concentrations of distilled water and sodium chloride in mixtures used in measuring surface tension of insulator surfaces in the range 73 mN/m to 82 mN/m ($T = 20^{\circ}\text{C}$) 14

INTRODUCTION

The wetting properties of a surface by water are commonly described by the terms hydrophobic (or hydrophobicity) and hydrophilic (or hydrophilicity). A hydrophobic surface is water-repellent, while a surface that is easily wetted by water is hydrophilic.

The wetting phenomenon of a surface is complex and many different parameters can influence its apparent wettability. Some important parameters include: type of insulator material, surface roughness, heterogeneities of the surface, chemical composition (e.g. due to ageing) and presence of pollution. For some of the insulator materials in common use, the wetting properties can change over time, due to the influence of the ambient conditions. This change can be either reversible or irreversible. Thus, the result of the measurement of the wettability may be influenced by the ambient conditions and the HV corona or dry-band arcing to which the insulator has been previously exposed. This dynamic wetting behaviour is more or less specific to different insulator materials.

The dynamic wetting behaviour exhibited by insulator materials is due to their chemical composition. Different processes such as oxidation, hydrolysis, migration of low molecular weight compounds, formation of complex compounds between e.g. siloxanes and water, rotation of flexible polymer chains, inter- and intra-molecular rearrangements, microbial growth, deposition of contaminants, adhesion and encapsulation of contaminant particles, may take place at different rates, depending on material and ambient conditions. Thus, wettability along and around an insulator can vary, due to differences in the exposure to solar radiation, rain, corona discharges, deposited pollution, etc. Therefore, wettability measurement of insulators should be performed on several separate areas of the insulator.

Measurement of the wettability of a surface is readily performed in the laboratory on well defined, homogeneous, smooth and planar surfaces of prepared specimens. In the case of insulators, for which non-destructive measurements are usually required (and where cut-out of material samples is usually not desired), these conditions do not exist and measurement with high precision is a difficult task. This is especially true when the measurement has to be performed on an insulator installed in an overhead line, substation or even in a high voltage test set-up in the laboratory.

NOTES

STANDARDS AUSTRALIA

Australian Standard**Guidance on the measurement of wettability of insulator surfaces**

1 Scope and object

The methods described in this technical specification can be used for the measurement of the wettability of the shed and housing material of composite insulators for overhead lines, substations and equipment or ceramic insulators covered or not covered by a coating. The obtained value represents the wettability at the time of the measurement.

The object of this standard is to describe three methods that can be used to determine the wettability of insulators. The determination of the ability of water to wet the surface of insulators may be useful to evaluate the condition of the surface of insulators in service, or as part of the insulator testing in the laboratory.

2 Terms and definitions

For the purposes of this document, the following definitions apply.

2.1**wettability**

ability of a surface to be wetted by a liquid (e.g. water)

2.2**hydrophobicity and hydrophilicity****2.2.1****hydrophobicity**

low level of wettability by water of a surface. A hydrophobic surface has a low surface tension and thus is water-repellent

2.2.2**hydrophilicity**

high level of wettability by water of a surface. A hydrophilic surface has a high surface tension and thus is wetted by water (in the form of a film)

2.3**surface tension**

interface tension

region of finite thickness (usually less than 0,1 μm) in which the composition and energy vary continuously from one bulk phase to the other. The pressure (force field) in the interfacial zone has a gradient perpendicular to the interfacial boundary. A net energy is required to create an interface (surface) by transporting the matter from the bulk phase to the interfacial (surface) zone. The reversible work required to create a unit interfacial (surface) area is the surface tension and is defined thermodynamically as follows:

$$\gamma = \left(\frac{\partial G}{\partial A} \right)_{T,P,n}$$