

Australian Standard[®]

**PLASTICS PIPES AND FITTINGS
FOR GAS RETICULATION—
UNPLASTICIZED PVC (UPVC)**

**Part 1—PIPES
Part 2—FITTINGS**

[Title allocated by Defence Cataloguing Authority:
PIPES AND FITTINGS, PLASTICS (Unplasticized PVC (UPVC))
(NATO Supply Classification: 4710 and 4730)]

This Australian standard was prepared by Committee PL/25, Plastics Pipe and Fittings for Gas Reticulation. It was approved on behalf of the Council of the Standards Association of Australia on 18 January 1984 and published on 11 May 1984.

The following interests are represented on Committee PL/25:

Australian Gas Association
Confederation of Australian Industry
Department of Minerals and Energy, Victoria
Department of Mines, Queensland
Federated Master Plumbers of Australia
Plastics Institute of Australia Inc.
State Energy Commission of Western Australia

Review of Australian Standards. *To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.*

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This standard was issued in draft form for comment as DR 83009 and 83010.

Australian Standard[®]

**PLASTICS PIPES AND FITTINGS
FOR GAS RETICULATION—
UNPLASTICIZED PVC (UPVC)**

**Part 1—PIPES
Part 2—FITTINGS**

First published	1974
Second edition	1984
Incorporating: Amdt 1—1986	

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 3349 8

PREFACE

This edition of this standard was prepared by the Association's Committee on Plastics Pipe and Fittings for Gas Reticulation to supersede AS 1464—1974. It sets out dimensional and performance requirements for UPVC pipes and fittings for use in gas reticulation systems. It also takes into consideration specific requirements of the gas industry in respect to terminology and gas pressure classification.

In this standard, pipes and fittings are designated by a nominal size as shown in Table 2.1. Designated sizes are not exact dimensions.

The standard classifies pipe as Type 1—Unmodified UPVC Class 100, and Type 2—Modified (improved impact) UPVC Class 100, for use underground with pressures up to 100 kPa and temperatures up to 40°C. New developments have taken place since the publication of the 1974 edition and an additional type has now been included, viz Type 3—Modified (high ductility) UPVC Class 100 and 450. Class 100 is for use with pressures up to 100 kPa and Class 450 for pressures up to 450 kPa, with temperatures up to 40°C.

It has been recognized that in the low pressure application, long-term hoop stress could no longer be used as the basis of design. Hoop stresses developed in the pipe wall due to internal pressure are quite low, and the predominant design consideration relates to the higher safety factors required by the industry because of the hazardous nature of the material conveyed.

The committee recognizes the need for test(s) of fracture toughness properties of UPVC to assess the likelihood of propagation failure during pressure testing and slow crack growth from notches occurring in the system. However there does not appear to be any positive relationship between resistance to these two forms of failure and further work is necessary to formulate suitable test(s).

A minimum wall thickness of 1.6 mm has been specified in this standard, but the dimensions are otherwise based on those established in AS 1477 for UPVC pipes and fittings for pressure applications.

Because permeability of UPVC to methane is negligible, no requirement for the determination of methane permeability has been included in the standard.

Polyethylene pipes and fittings for gas reticulation are specified in AS 1667, Plastics Pipes and Fittings for Gas Reticulation—Polyethylene—Nominal Size Series*, and AS, Plastics Pipes and Fittings for Gas Reticulation—Polyethylene—ISO Outside Diameter Series†.

* Under revision.

† In course of preparation.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

Page

PART 1—PIPES

SECTION 1. SCOPE AND GENERAL

1.1	Scope	4
1.2	Referenced Documents	4
1.3	Definitions	4
1.4	Notation	5
1.5	Classification	5
1.6	Pressure Ratings of Classes	5

SECTION 2. COMPOSITION AND DIMENSIONS

2.1	Composition	6
2.2	Pipe Dimensions	6
2.3	Pipe Spigot Ends	6
2.4	Sockets Formed on Pipe Ends	6
2.5	Freedom From Defects	6

SECTION 3. TEST REQUIREMENTS

3.1	Flattening	8
3.2	Impact Characteristics At 20°C	8
3.3	Impact Characteristics At 0°C	8
3.4	Reversion	8
3.5	Softening Point	8
3.6	Anhydrous Acetone Immersion	8
3.7	Chemical Resistance	8
3.8	Hydrostatic Pressure Tests	8
3.9	Squeeze-off Properties	8

SECTION 4. MARKING, STORAGE AND TRANSPORT

4.1	Marking	10
4.2	Storage and Transport	10

APPENDICES

A	Determination of Compliance of a Lot	11
B	Method For Determining Weathering Resistance	13
C	Method For Determining Chemical Resistance	14
D	Method of Test For Squeeze-off Properties of Pipe	16

PART 2—MOULDED FITTINGS

1	SCOPE	17
2	REFERENCED DOCUMENTS	17
3	NOTATION	17
4	CLASSIFICATION	17
5	COMPLIANCE	17
6	GENERAL REQUIREMENTS	17
7	CHEMICAL RESISTANCE	18
8	MARKING, STORAGE AND TRANSPORT	18

APPENDIX A.	DETERMINATION OF COMPLIANCE OF A LOT	19
-------------	--	----

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard

for

PLASTICS PIPES AND FITTINGS FOR GAS RETICULATION—UNPLASTICIZED
PVC (UPVC)

PART 1—PIPES

SECTION 1. SCOPE AND GENERAL

1.1 SCOPE. This standard specifies requirements for UPVC pipes for use in gas mains and services for direct burial and refiner applications. Such pipe is intended for use with natural gas, liquefied petroleum gas (LP gas), and air and LP gas mixtures at pressures up to 450 kPa.

This standard does not apply to pipe for use with petroleum liquids, including liquid LP gas and pentane, manufactured or mixed gas distribution systems, systems which may contain more than 1 percent ammonia, or systems in which the gas contains more than 50 percent saturation vapour pressure of aromatics.

Pipes manufactured in accordance with this standard are intended to be jointed using solvent cements complying with AS XXXX.

NOTES:

- AS YYYY is applicable to pipes manufactured in accordance with this standard.
- Fittings for use with pipes specified in this standard are dealt with in AS 1464, Part 2.
- Advisory information on alternative methods of determining compliance of a lot with this standard is given in Appendix A.

1.2 REFERENCED DOCUMENTS. The following standards are referred to in this standard:

AS 1145	Method for Determination of Tensile Properties of Plastics Materials
AS 1199	Sampling Procedures and Tables for Inspection by Attributes
AS 1399	Guide to AS 1199, Sampling Procedures and Tables for Inspection by Attributes
AS 1462	Methods of Test for Unplasticized PVC (UPVC) Pipes and Fittings
AS 1462.1	Method for Determining the Dimensions of UPVC Pipes and Fittings
AS 1462.2	Method for Determining the Flattening Properties of UPVC Pipes
AS 1462.3	Method for Determining the Impact Characteristics of UPVC Pipes
AS 1462.4	Method for Determining Reversion of UPVC Pipes
AS 1462.5	Method for Determining the Softening Point of UPVC Pipes and Fittings
AS 1462.6	Method for Hydrostatic Pressure Testing of UPVC Pressure Pipes

AS 1462.12 Method for Determining the Effect of Immersion in Anhydrous Acetone on UPVC Pipes

AS 1821-23 Suppliers Quality Control Systems—Levels 1, 2 and 3

AS 2000 Guide to AS 1821-23, Suppliers Quality Control Systems

AS 2032 Installation of UPVC Pipe Systems

AS 2193 Methods for Calibration and Grading of Force-measuring Systems of Testing Machines

AS 2490 Sampling Procedures and Charts for Inspection by Variables for Percent Defective

AS XXXX Solvent Cements and Priming Fluids for use with Unplasticized PVC Pipe and Fittings*

AS YYYY Installation of Plastics Gas Pipe Systems*

BS 381C Colours for Specific Purposes.

1.3 DEFINITIONS. For purposes of this standard, the following definitions apply:

1.3.1 LP gas—liquefied petroleum gas which is composed predominantly of any of the following hydrocarbons or mixtures of all or any of them: propane, propylene, butanes and butylenes.

1.3.2 Hoop stress—the stress in a pipe or fitting under pressure acting tangentially to the perimeter of a transverse section.

1.3.3 Long-term hydrostatic stress—the continuously applied hoop stress which is estimated will cause failure at a specified time and temperature.

1.3.4 Hydrostatic design stress—the estimated hoop stress due to internal hydrostatic pressure that can be applied continuously at a specified temperature with a high degree of certainty that failure will not occur. It is obtained by the application of a safety factor to the extrapolated 50-year long-term hydrostatic stress value.

1.3.5 Type test—a test intended to prove the suitability and performance of a new composition, a new compounding or processing technique, or a new design or size of pipe, joint or fitting. Type tests are generally carried out when a change is made in polymer composition or method of manufacture.

* In course of preparation.