

Australian Standard™

**Welding—Guide on the measurement of
preheating temperature, interpass
temperature and preheat maintenance
temperature**

This Australian Standard was prepared by Committee WD-003, Welding of Structures. It was approved on behalf of the Council of Standards Australia on 11 April 2003 and published on 27 June 2003.

The following are represented on Committee WD-003:

Australian Chamber of Commerce and Industry
Australian Industry Group
AUSTROADS
Bureau of Steel Manufacturers of Australia
Electricity Supply Association of Australia
Institution of Engineers Australia
New Zealand Heavy Engineering Research Association
New Zealand Non-destructive Testing Association
New Zealand Welding School
Steel Reinforcement Institute of Australia
University of Sydney
Welding Technology Institute of Australia

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Global Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.com.au, or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

This Standard was issued in draft form for comment as DR 03088.

Australian Standard™

**Welding—Guide on the measurement of
preheating temperature, interpass
temperature and preheat maintenance
temperature**

First published as AS ISO 13916—2003.

COPYRIGHT

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 5255 1

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee WD-003, Welding of Structures. It is technically identical to, and reproduced from ISO 13916:1996, *Welding—Guidance on the measurement of preheating temperature, interpass temperature and preheat maintenance temperature*.

After consultation with stakeholders on both countries, Standards Australia and Standards New Zealand decided to develop this Standard as an Australian Standard rather than an Australian/New Zealand Standard.

As this Standard is reproduced from an international Standard, the following applies:

- (a) Its number appears on the cover and title page while the International Standard number appears only on the cover.
- (b) In the source text ‘this International Standard’ should read ‘this Australian Standard’.

FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 13916 was prepared by the European Committee for Standardization (CEN) in collaboration with ISO Technical Committee TC 44, *Welding and allied processes*, Subcommittee SC 10, *Unification of requirements in the field of metal welding*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

CONTENTS

	page
Foreword.....	iv
1 Scope	1
2 Definitions.....	1
2.1 Preheating temperature (T_p).....	1
2.2 Interpass temperature (T_i).....	1
2.3 Preheat maintenance temperature (T_m).....	1
3 Requirements.....	1
3.1 Point of measurement.....	1
3.2 Time of measurement.....	2
3.3 Test equipment	3
4 Test report	3
5 Designation.....	3

AUSTRALIAN STANDARD

Welding—Guide on the measurement of preheating temperature, interpass temperature and preheat maintenance temperature**1 Scope**

This standard specifies requirements for the measurement of preheating temperature, interpass temperature and preheat maintenance temperature for fusion welding. This standard may also be applied as appropriate in the case of other welding processes. This standard does not cover the measurement of post weld heat treatment temperatures.

2 Definitions

For the purposes of this standard the following definitions apply:

2.1 preheating temperature (T_p): the temperature of the workpiece in the weld zone immediately prior to any welding operation. It is normally expressed as a minimum and is usually equal to the minimum interpass temperature.

2.2 interpass temperature (T_i): the temperature in a multi-run weld and adjacent parent metal immediately prior to the application of the next run. It is normally expressed as a maximum temperature.

2.3 preheat maintenance temperature (T_m): the minimum temperature in the weld zone which shall be maintained if welding is interrupted.

3 Requirements**3.1 Point of measurement**

The temperature measurement shall normally be made on the surface of the workpiece facing the welder, at a distance of $A = 4 \times t$, but not more than 50 mm, from the longitudinal edge of the groove (see figure 1). This shall apply for workpieces thickness t not exceeding 50 mm in the weld.

When the thickness exceeds 50 mm, the required temperature shall exist in the parent metal for a distance of at least 75 mm or as otherwise agreed in any direction from the joint preparation. Where practicable, the temperature shall be measured on the face opposite to that being heated. Otherwise, the temperature shall be confirmed on the heated face at a time after removal of the heat source related to parent metal thickness to allow for temperature equalization. Where fixed permanent heaters are in use and there is no access to the reverse face for temperature measurement, readings shall be taken on the exposed parent metal surface immediately adjacent to the weld preparation. The time allowed for the temperature equalization shall be of the order of 2 min for each 25 mm of parent metal thickness.

Interpass temperature shall be measured on the weld metal or the immediately adjacent parent metal.