



Copper, lead, zinc and nickel concentrates—Sampling of slurries



This Australian Standard® was prepared by Committee MN-005, Copper, Lead, Zinc and Nickel Ores and Concentrates. It was approved on behalf of the Council of Standards Australia on 26 August 2015.

This Standard was published on 29 September 2015.

The following are represented on Committee MN-005:

- Australasian Institute of Mining and Metallurgy
 - CSIRO
 - Minerals Council of Australia
-

This Standard was issued in draft form for comment as DR AS ISO 11794:2015.

Standards Australia wishes to acknowledge the participation of the expert individuals that contributed to the development of this Standard through their representation on the Committee and through the public comment period.

Keeping Standards up-to-date

Australian Standards® are living documents that reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued.

Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments that may have been published since the Standard was published.

Detailed information about Australian Standards, drafts, amendments and new projects can be found by visiting www.standards.org.au

Standards Australia welcomes suggestions for improvements, and encourages readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.org.au, or write to Standards Australia, GPO Box 476, Sydney, NSW 2001.

Australian Standard[®]

**Copper, lead, zinc and nickel
concentrates—Sampling of slurries**

First published as AS ISO 11794:2015.

COPYRIGHT

© Standards Australia Limited

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968.

Published by SAI Global Limited under licence from Standards Australia Limited, GPO Box 476, Sydney, NSW 2001, Australia

ISBN 978 1 76035 252 3

PREFACE

This Standard was prepared by the Standards Australia Committee MN-005 Copper, Lead, Zinc and Nickel Ores and Concentrates.

The objective of this Standard is to set out the basic methods for sampling particulate material that is mixed with a liquid, usually water, to form a slurry. In industry and in the mining and mineral processing literature, slurry is also referred to as pulp, but this term is not used in this standard. At very high ratios of fine particulate solids to liquids where material assumes a soft plastic form, the mixture is correctly termed as a paste. Sampling of pastes is not covered in this standard.

This Standard is identical with, and has been reproduced from ISO 11794:2010, *Copper, lead, zinc and nickel concentrates—Sampling of slurries*.

As this Standard is reproduced from an International Standard, the following applies:

- (a) In the source text ‘this International Standard’ should read ‘this Australian Standard’.
- (b) A full point substitutes for a comma when referring to a decimal marker.

References to International Standards should be replaced by references to Australian or Australian/New Zealand Standards, as follows:

<i>Reference to International Standard</i>	<i>Australian Standard</i>
ISO	AS
	2862 Copper, lead, zinc and nickel concentrates—Sampling
12743 Copper, lead, zinc and nickel concentrates—Sampling procedures for determination of metal and moisture content	2862.1 Part 1: Sampling procedures for determination of metal and moisture content
12744 Copper, lead, zinc and nickel concentrates—Experimental methods for checking the precision of sampling	2862.2 Part 2: Experimental methods for checking the precision of sampling
13292 Copper, lead, zinc and nickel concentrates—Experimental methods for checking the bias of sampling	2862.3 Part 3: Experimental methods for checking the bias of sampling

Only normative references that have been adopted as Australian or Australian/New Zealand Standards have been listed.

The terms ‘normative’ and ‘informative’ have been used in this Standard to define the application of the annexes to which they apply. A ‘normative’ annex is an integral part of a Standard, whereas an ‘informative’ annex is only for information and guidance.

CONTENTS

1	Scope	1
2	Normative references	1
3	Terms and definitions	2
4	Principles of sampling slurries	2
4.1	General	2
4.2	Sampling errors	3
4.2.1	General	3
4.2.2	Preparation error, PE	4
4.2.3	Delimitation and extraction errors, DE and EE	4
4.2.4	Weighting error, WE	6
4.2.5	Periodic quality-fluctuation error, QE_3	6
4.3	Sampling and total variance	6
4.3.1	Sampling variance	6
4.3.2	Total variance	6
4.3.3	Sampling-stage method of estimating sampling and total variance	8
4.3.4	Simplified method of estimating sampling and total variance	9
4.3.5	Interleaved sample method of measuring total variance	10
5	Establishing a sampling scheme	11
6	Minimization of bias and unbiased increment mass	16
6.1	Minimization of bias	16
6.2	Volume of increment for falling-stream samplers to avoid bias	17
7	Number of increments	17
7.1	General	17
7.2	Simplified method	18
8	Minimum mass of solids contained in lot and sub-lot samples	18
8.1	Minimum mass of solids in lot samples	18
8.2	Minimum mass of solids in sub-lot samples	18
8.3	Minimum mass of solids in lot and sub-lot samples after size reduction	18
9	Time-basis sampling	19
9.1	General	19
9.2	Sampling interval	19
9.3	Cutters	19
9.4	Taking of increments	19
9.5	Constitution of lot or sub-lot samples	20
9.6	Division of increments and sub-lot samples	20
9.7	Division of lot samples	20
9.8	Number of cuts for division	20
10	Stratified random sampling within fixed time intervals	20
11	Mechanical sampling from moving streams	21
11.1	General	21
11.2	Design of the sampling system	21
11.2.1	Safety of operators	21
11.2.2	Location of sample cutters	21
11.2.3	Provision for duplicate sampling	21
11.2.4	System for checking the precision and bias	21
11.2.5	Avoiding bias	22

11.3	Slurry sample cutters	22
11.3.1	General.....	22
11.3.2	Falling-stream cutters	23
11.3.3	Cutter velocities	23
11.4	Mass of solids in increments.....	23
11.5	Number of primary increments	23
11.6	Routine checking.....	23
12	Manual sampling from moving streams.....	24
12.1	General.....	24
12.2	Choosing the sampling location	24
12.3	Sampling implements.....	25
12.4	Mass of solids in increments.....	25
12.5	Number of primary increments	25
12.6	Sampling procedures	25
13	Sampling of stationary slurries	26
14	Sample preparation	26
14.1	General.....	26
14.2	Sample division.....	26
14.3	Sample grinding.....	26
14.4	Chemical analysis samples	26
14.5	Physical test samples	27
15	Packing and marking of samples.....	27
Annex A	(normative) Sampling-stage method for estimating sampling and total variance	28
Annex B	(informative) Examples of correct slurry sampling devices	34
Annex C	(informative) Examples of incorrect slurry sampling devices	37
Annex D	(normative) Manual sampling implements.....	41
Bibliography	42

AUSTRALIAN STANDARD

Copper, lead, zinc and nickel concentrates—Sampling of slurries

WARNING — This International Standard may involve hazardous materials, operations and equipment. It is the responsibility of the user of this International Standard to establish appropriate health and safety practices and determine the applicability of regulatory limitations prior to use.

1 Scope

This International Standard sets out the basic methods for sampling particulate material that is mixed with a liquid, usually water, to form a slurry. In industry and in the mining and mineral processing literature, slurry is also referred to as pulp, but this term is not used in this International Standard. At very high ratios of fine particulate solids to liquids where material assumes a soft plastic form, the mixture is correctly termed as a paste. Sampling of pastes is not covered in this International Standard.

The procedures described in this International Standard apply to sampling of particulate materials that are transported in moving streams as slurries, but not pressurized slurries. These streams may fall freely or be confined in pipes, launders, flumes, sluices, spirals or similar channels. Sampling of slurries in stationary situations, such as a settled or even a well-stirred slurry in a holding vessel or dam, is not recommended and is not covered in this International Standard.

This International Standard describes procedures that are designed to provide samples representative of the slurry solids and particle-size distribution of the slurry under examination. After draining the slurry sample of fluid and measuring the fluid volume, damp samples of the contained particulate material in the slurry are available for drying (if required) and measurement of one or more characteristics in an unbiased manner and with a known degree of precision. The characteristics are measured by chemical analysis, physical testing or both.

The sampling methods described are applicable to slurries that require inspection to verify compliance with product specifications, determination of the value of a characteristic as a basis for settlement between trading partners or estimation of a set of average characteristics and variances that describes a system or procedure.

Provided that flow rates are not too high, the reference method against which other sampling procedures are compared is one where the entire stream is diverted into a vessel for a specified time or volume interval. This method corresponds to the stopped-belt method described in ISO 12743.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 12743, *Copper, lead, zinc and nickel concentrates — Sampling procedures for determination of metal and moisture content*

ISO 12744, *Copper, lead, zinc and nickel concentrates — Experimental methods for checking the precision of sampling*